

## Vulcabond™ TP

Single component Bonding Agent for PVC plastisols coated onto polyamide or polyester

<b>Vulcabond</b>	<b>TP</b>
Type	Bonding Agent
Appearance	Pale yellow liquid
Viscosity at 25°C Pas	2.6
Active ingredient %	25
Flash point °C closed cup	>100°C
Free NCO %	4.0
Free TDI %	< 1%

*These are typical values*

## Vulcabond

Vulcabond bonding agents are used in PVC plastisols when coated onto woven polyester or polyamides such as nylon to prevent material failure caused by delamination of the PVC coating. Vulcabond products are single component bonding agents and with careful selection of stabilisers, viscosity modifiers, PVC grades and fabric type will ensure optimum pot life viscosity during coating and good coating adhesion throughout its service life. The free NCO content is a measure of the amount of active groups available for bonding to fabric.

End products containing bonding agents include marquees, awnings, truck sidings, tarpaulins conveyor belting, outdoor clothing and printed tee shirts.

## Performance

Vulcabond TP contains 25% polyisocyanurate and is based on a phthalate-free carrier. Typical addition level is 4-8% in plastisol formulations.

## Supplementary Information

The length of stability and colour control can be further improved when used in conjunction with an epoxy plasticiser, such as Lankroflex E2307 or Lankroflex ED6 (3.0 to 5.0 phr). Lankroflex ED6 helps to maintain low plastisol viscosity during coating. Biocide products from the Intercide range are often used in this application to prevent fungal and bacterial growth on the coated fabric.

## Packaging, Storage & Handling

Vulcabond TP is supplied in drums of approximate nett weight 210kg. Storage at room temperature is recommended. Vulcabond products are sensitive to water so once opened, drums should be firmly closed after use. Full information on the safe handling of this product is available on the Health and Safety Data Sheet.



#### Disclaimer

Any analytical or technical work undertaken by us/Valtris for you is confidential and for your own reference or internal purposes. If you wish to send a copy of this work to a third party then you must seek our prior written consent. All information, recommendations and suggestions appearing in this literature concerning the use of products are based upon tests and data believed to be reliable, however, Valtris Specialty Chemicals gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose of the contents of such literature. It is the users responsibility to determine the suitability for its own use of the products described in such literature. No guarantee (whether express or implied ) is made by Valtris Specialty Chemicals as to the results to be obtained from using the described products, nor shall Valtris Specialty Chemicals be liable for any use by others of the described products. Additional information to that described in this literature may be required, for example, when particular or exceptional conditions or circumstances are contemplated or because of relevant laws or government regulations. Nothing in this literature shall be construed as authorisation or recommendation to infringe any patent. All orders accepted shall be subject to the standard conditions of sale of the manufacturer, Valtris Specialty Chemicals

Valtris Specialty Chemicals, Lankro Way, Eccles, Manchester, UK, M30 0LX.

Tel +441617851111

---

[www.valtris.com](http://www.valtris.com)